

Total Lak Uhs

1398

FAST ACRYLIC UHS CLEAR-COAT



Packaging

Colour	Unit si	ze	Pcs/box
0000 Transparent	5L	Α	2
0000 Hardener	2,5 L	В	2
0000 Transparent	1 L	Α	6
0000 Hardener	0,5 L	В	6

Curing ratio: 2:1 in volume

Hardener B: 4376 STANDARD UHS, 4386 SLOW UHS

Two-component acrylic transparent varnish, non-yellowing, excellent quality, with high content of solid substances (COV content less than 420 g/l). Thanks to its easy applicability and versatility, it's possible to increase productivity while always obtaining excellent results.

- → Easy applicability
- → With high content of solid substances
- → Suitable for small surfaces or complete painting

Application

It can be used for double coat finishes on matt pastel and metallised bases, both water and solvent based.

Tools

Spray gun

Technical data

Pot-life	50 ÷ 60 min
Dry film appearance	Glossy, > 95 gloss Gardner 60°
Dust free	20 min
Handling	4 h
Through drying	24 h
Oven at 50°C	20 min
Recommended thickness	50 - 60 μm dry film
	. ,
→ Dilution	max 10% with 1653 DIL X ACRILICI
→ Cover rate	8 - 9 m ² /l with 2 coats

Hardener

The choice of the suitable hardener must be made based on the work to be performed. For a few panels / small surfaces it is possible to use the standard hardener code 4376. We do not recommend using this hardener at high temperatures and on flat and large surfaces. For complete painting / many panels, with high temperatures and on flat and large surfaces, we suggest the use of slow hardener code 4386.

Small or medium restore (1 – 5 panels)



Total restore or in case of high temperatures





AUTHORIZED DEALER

IMPA S.p.A. Unipersonale – Via Crevada, 9/E 31020 San Pietro di Feletto TV – ITALY T +39 0438 4548 F + 39 0438 454915 info@impa.it – www.impa.it